

Príloha P VI Naměřená data jasanových vzorků

	Obsah vody v dřevině [%]		
Č.m.	Doma	Venku	Voda
1.	6,6	10,4	15,5
2.	7,4	10,1	15,3
3.	8,6	11,4	15,2
4.	8,5	10,9	16,1
5.	9,2	10,9	15,3
Průměr	8,1	10,7	15,5
Smdch	1,04	0,50	0,36

Výška jasanového hranolu měřena plochým hrotem [mm]				
	DOMA	VENKU	VODA	
1.	25,647	25,550	25,665	
2.	25,727	25,558	25,673	
3.	25,645	25,519	25,706	
4.	25,619	25,511	25,660	
5.	25,680	25,541	25,663	
6.	25,697	25,542	25,722	
7.	25,650	25,531	25,646	
8.	25,640	25,636	25,738	
9.	25,670	25,619	25,721	
10.	25,611	25,555	25,638	
Průměr	25,659	25,556	25,683	
Smdch	0,0355	0,0406	0,0354	
Median	25,649	25,546	25,669	

Výška dřevěného jasanového hranolu plochým hrotem					
	JASAN-DOMA [mm]				
Č.M.	30/100 [W]	40/100 [W]	50/100 [W]	60/100 [W]	70/100 [W]
1.	25,480	25,454	25,418	25,288	25,313
2.	25,488	25,435	25,447	25,311	25,322
3.	25,490	25,467	25,461	25,338	25,361
4.	25,475	25,478	25,444	25,317	25,347
5.	25,481	25,464	25,425	25,304	25,351
Průměr	25,483	25,460	25,439	25,312	25,339
Smdch	0,006	0,016	0,017	0,018	0,020
Median	25,481	25,464	25,444	25,311	25,347

Hloubka odstraněné vrstvy [mm]				
30/100 [W]	40/100 [W]	50/100 [W]	60/100 [W]	70/100 [W]
0,176	0,199	0,220	0,347	0,320

	JASAN-VENKU [mm]				
Č.M.	30/100 [W]	40/100 [W]	50/100 [W]	60/100 [W]	70/100 [W]
1.	25,482	25,379	25,276	25,205	25,155
2.	25,481	25,432	25,344	25,233	25,176
3.	25,512	25,421	25,306	25,253	25,186
4.	25,503	25,383	25,280	25,214	25,171
5.	25,463	25,377	25,259	25,205	25,167
Průměr	25,488	25,398	25,293	25,222	25,171
Smdch	0,019	0,026	0,033	0,021	0,011
Median	25,482	25,383	25,280	25,214	25,171

Hloubka odstraněné vrstvy [mm]				
30/100 [W]	40/100 [W]	50/100 [W]	60/100 [W]	70/100 [W]
0,068	0,158	0,263	0,334	0,385

	JASAN-VODA [mm]				
Č.M.	30/100 [W]	40/100 [W]	50/100 [W]	60/100 [W]	70/100 [W]
1.	25,543	25,540	25,467	25,454	25,369
2.	25,554	25,529	25,483	25,418	25,366
3.	25,562	25,529	25,492	25,453	25,381
4.	25,554	25,524	25,442	25,439	25,367
5.	25,537	25,509	25,450	25,395	25,358
Průměr	25,550	25,526	25,467	25,432	25,368
Smdch	0,010	0,011	0,021	0,025	0,008
Median	25,554	25,529	25,467	25,439	25,367

Hloubka odstraněné vrstvy [mm]				
30/100 [W]	40/100 [W]	50/100 [W]	60/100 [W]	70/100 [W]
0,133	0,157	0,216	0,251	0,315

Výška jasanového hranolu měřena špičatým hrotem [mm]				
	DOMA	VENKU	VODA	
1.	25,656	25,598	25,620	
2.	25,654	25,605	25,639	
3.	25,646	25,568	25,664	
4.	25,608	25,550	25,616	
5.	25,677	25,504	25,597	
6.	25,596	25,532	25,610	
7.	25,597	25,503	25,636	
8.	25,619	25,456	25,691	
9.	25,571	25,502	25,668	
10.	25,518	25,522	25,631	
Průměr	25,614	25,534	25,637	
Smdch	0,0473	0,0467	0,0293	
Median	25,614	25,527	25,634	

Výška dřevěného jasanového hranolu špičatým hrotem					
	JASAN-DOMA [mm]				
Č.M.	30/100 [W]	40/100 [W]	50/100 [W]	60/100 [W]	70/100 [W]
1.	25,275	25,255	25,112	25,206	24,945
2.	25,260	25,307	25,182	24,968	24,964
3.	25,290	25,306	25,078	25,011	25,052
4.	25,320	25,251	25,231	25,091	25,094
5.	25,360	25,275	25,179	25,028	25,140
6.	25,365	25,251	25,237	25,109	25,076
7.	25,324	25,274	25,304	25,135	25,103
8.	25,283	25,243	25,196	25,065	25,085
9.	25,383	25,179	25,292	24,970	24,982
10.	25,374	25,262	25,255	25,036	25,170
Průměr	25,323	25,260	25,207	25,062	25,061
Smdch	0,045	0,036	0,073	0,075	0,075
Median	25,322	25,259	25,214	25,051	25,081

Hloubka odstraněné vrstvy [mm]				
30/100 [W]	40/100 [W]	50/100 [W]	60/100 [W]	70/100 [W]
0,291	0,354	0,408	0,552	0,553

	JASAN-VENKU [mm]				
Č.M.	30/100 [W]	40/100 [W]	50/100 [W]	60/100 [W]	70/100 [W]
1.	25,274	25,222	25,072	24,930	24,888
2.	25,256	25,068	25,052	24,895	24,751
3.	25,300	25,103	25,066	24,939	24,638
4.	25,281	25,160	25,060	24,889	24,832
5.	25,369	25,037	25,078	24,819	24,784
6.	25,288	25,047	24,956	24,858	24,731
7.	25,313	25,098	24,932	25,164	24,764
8.	25,291	25,087	24,913	24,929	24,867
9.	25,264	25,177	24,992	25,109	24,783
10.	25,268	25,179	25,036	24,912	24,813
Průměr	25,290	25,118	25,016	24,944	24,785
Smdch	0,033	0,063	0,062	0,108	0,072
Median	25,285	25,101	25,044	24,921	24,784

Hloubka odstraněné vrstvy [mm]				
30/100 [W]	40/100 [W]	50/100 [W]	60/100 [W]	70/100 [W]
0,244	0,416	0,518	0,590	0,749

	JASAN-VODA [mm]				
Č.M.	30/100 [W]	40/100 [W]	50/100 [W]	60/100 [W]	70/100 [W]
1.	25,382	25,288	25,164	24,976	24,888
2.	25,365	25,253	25,178	25,130	24,751
3.	25,435	25,274	25,215	25,141	24,638
4.	25,448	25,250	25,123	24,962	24,832
5.	25,442	25,280	25,101	25,037	24,784
6.	25,435	25,255	25,208	25,009	24,731
7.	25,319	25,208	25,081	25,041	24,764
8.	25,356	25,222	25,135	25,047	24,867
9.	25,344	25,356	25,106	25,053	24,783
10.	25,417	25,321	25,054	25,082	24,813
Průměr	25,394	25,271	25,137	25,048	24,785
Smdch	0,047	0,044	0,054	0,059	0,072
Median	25,400	25,265	25,129	25,044	24,784

Hloubka odstraněné vrstvy [mm]				
30/100 [W]	40/100 [W]	50/100 [W]	60/100 [W]	70/100 [W]
0,243	0,366	0,501	0,589	0,852